

УДК 54-12

doi:10.20998/2413-4295.2018.26.35

QUANTUM-CHEMICAL MODELING OF MOLECULAR COMPLEXES STRUCTURE IN "URONATIC POLYSACCHARIDES – Ca²⁺" SYSTEM

N. KONDRATJUK*¹, E. PIVOVAROV², T. STEPANOVA³, D. TOLOSHNYI¹, Y. POLYVANOV¹

¹ Department of Food Technology Oles Honchar Dnipro National University, Dnipro, UKRAINE

² Professor, Doctor of Technical Sciences Department of Technology of the Food, Kharkiv State University of Food and Trade, Kharkiv, UKRAINE

³ Associate Professor at the Department of Food Technologies, Sumy National Agrarian University, Sumy, UKRAINE

*email: kondratjuk3105@gmail.com

ABSTRACT Quantum-chemical modeling of the process of ionotropic gelling in systems of uronate polysaccharides (high-guluronate sodium alginate and low-esterified pectin) with calcium is carried out. Calculation the interaction of active functional groups of uronate polysaccharides with calcium ion shows the possibility of this process passage through the formation of calcium-guluronate (CaGal₄), calcium-galacturonate (CaGal₄) and calcium-guluronate-galacturonate (CaGal₂Gal₂) chelate complexes.

The process of interaction occurs when the carboxyl and hydroxyl groups of the uronate polysaccharides are chemically bound to the calcium ion. It was established that calcium-guluronate complex has an eight binding centres with calcium whereas calcium-galacturonate and calcium-guluronate-galacturonate complexes have four binding centres.

This article describes the binding centres in systems that are considered by ionotropic gel formation. This clearly illustrated the spatial atoms arrangement in the systems of individual polysaccharides and their combination; location and value of bond lengths, values of torsion and valence angles. Presented quantum-chemical models are allowed to estimate chemical activity of fragments macromolecular structures during ionotropic gelation. This makes it possible to predict the amount of external bound water, calculate the optimum proportions of substances for the formulation of rational food recipes.

The fact of the ionotropic gelation in the combined system "alginate-pectin-Ca" was installed on the basis of the obtained models and their geometric characteristics. In this case the chelate complexes CaGal₂Gal₂ was formed. It is stable during storage, more plastic and soft in contrast to CaGal₄ and stronger than CaGal₄.

Keywords: alginate; pectin; complex formation; quantum-chemical modeling.

КВАНТОВО-ХИМИЧЕСКОЕ МОДЕЛИРОВАНИЕ СТРУКТУР МОЛЕКУЛЯРНЫХ КОМПЛЕКСОВ В СИСТЕМЕ «УРОНАТНЫЕ ПОЛИСАХАРИДЫ – Ca²⁺»

Н. В. КОНДРАТЮК¹, Е. П. ПИВОВАРОВ², Т. М. СТЕПАНОВА³, Д. В. ТОЛОШНЫЙ¹,
Е. А. ПОЛИВАНОВ¹

¹ Дніпровський національний університет імені Олеса Гончара, г. Дніпр, УКРАЇНА

² д.т.н., професор, Харківський державний університет харчування та торгівлі, г. Харків, УКРАЇНА

³ к.т.н., доцент, Сумської національний аграрний університет, г. Суми, УКРАЇНА

АННОТАЦИЯ Проведено квантово-химическое моделирование процесса ионотропного гелеобразования в системах уронатных полисахаридов (альгината натрия высокогулуронатного и пектина низкоэтерифицированного) с кальцием. Расчет взаимодействия активных функциональных групп уронатных полисахаридов с ионом кальция показывает возможность прохождения данного процесса с образованием хелатных комплексов кальций-гулуронатного, кальций-галактуронатного и кальций-гулуронат-галактуронатного.

Процесс взаимодействия осуществляется за счет химического связывания карбоксильных и гидроксильных групп уронатных полисахаридов с ионом кальция. Установлено, что кальций-гулуронатный комплекс имеет восемь центров связывания с кальцием, а комплексы кальций-галактуронатный и кальций-гулуронат-галактуронатный имеют по четыре центра связывания.

В статье приводится описание центров химического связывания в рассматриваемых системах при реализации принципа ионотропного гелеобразования. Наглядно представлено пространственное расположение множества атомов в системах отдельных полисахаридов и их комбинации; расположение и величины длин связей, значения торсионных и валентных углов. Представленные квантово-химические модели позволяют оценить химическую активность фрагментов структур макромолекул в случае протекания химических процессов ионотропного гелеобразования и дает возможность спрогнозировать количество внешнесвязанной воды, рассчитать оптимальные соотношения веществ для составления рациональных рецептур пищевых продуктов.

На основании полученных моделей и их геометрических характеристик был установлен факт протекания процесса ионотропного гелеобразования в комбинированной системе «альгинат-пектин-Са». В этом случае, образовался хелатный комплекс CaGal₂Gal₂, устойчивый в ходе хранения, более пластичный и мягкий в отличие от CaGal₄ и более прочный в отличие от CaGal₄.

Ключевые слова: альгинат; пектин; комплексообразование; квантово-химическое моделирование.

Introduction

Modern representation of food systems based on quantum-chemical modeling, allows obtaining the

following results, important for the technological process organization:

1) derive an optimal ratio of the recipe components during the creating of food compositions;

2) choose the most appropriate conditions for the chemical potential realization of the large macromolecules reactive sites, such as proteins and polysaccharides;

3) carry out diagnostics of different binding centers on the possibility of the chemical, van der Waals interaction, hydration and mass transfer processes without costly investment into the experimental part;

4) obtain a general idea of the nutritional components and water role in the food compositions under consideration, for subsequent recommendations of chemical and physicochemical processes stabilization, associated with quality and safety indicators.

This article discusses systems based on sodium alginate (with an increased content of guluronate residues) and pectin (low esterified amidated) with realization of calcium ions chemical potential in various interaction with the remainders of uronic acids.

Calcium, as the most promising binding agent, and under consideration uronate polysaccharides, as widely used substances for obtaining gel-like systems with valuable food properties and technological characteristics, form firmly bound structures in food systems. These structures allow stabilizing the processes of moisture mass transfer and keep it to 30% when passing from the phase of the hydrogel to the xerogel [1].

Nowadays significant relevance is the study of polysaccharide compositions based on sodium alginate and pectin with other polysaccharides. For example, the authors [2] monitored the adsorption properties of the sodium alginate matrix with the participation of guar gum. The article [3] describes the molecular mechanism of lysozyme adsorption to a chemically modified alginate-guar matrix. New biodegradable and antibacterial edible films based on alginate hydrochloride and biguanidine chitosan are described in the article [4]. In the materials of the scientific publication [5] describe microgel of silylated (hydroxypropyl) methyl cellulose, which is considered as a multimodal system for the joint encapsulation of drugs. A group of scientists received alginate fibers coated with chitosan and described their antibacterial effect. [6].

The most obvious advantages are mixed pectin-alginate gels, structured by calcium ions [7, 8].

However, it should be noted, that systems based on this composition remain poorly researched, although they have a significant economic effect when used in various technologies [9-12].

Objects

The purpose of this work is the detailed elaboration of theoretical study the features of molecular complexes equilibrium structures, which are

implemented in the system «uronate polysaccharides – Ca^{2+} » by means of *ab initio* quantum chemistry methods.

Statement of the main material

Quantum chemical modeling is the method of obtaining the molecule electron energy and its wave function, which does not depend on the size and structure of the macromolecule.

It must be borne in mind three determining factors before the construction of a quantum chemical model. Namely, to select the components of the mathematical model, carry out a decision procedure and choose an atomic basis. Thus, to determine the method of obtaining the electron energy and the wave function [13].

The wave function is meant density matrix in density functional theory. It should be noted that this method does not describe any particular chemical system and can be applied to a molecule of any size and to any molecular structure and to any type of chemical binding. [14, 15].

Quantum-chemical models CaGal_4 , CaGal_4 , $\text{CaGal}_2\text{Gal}_2$, presented on the Figure 1 a-c were obtained on the basis of this.

Named images confirm the uniqueness of the Schrödinger equation solution for a given nuclei configuration, electron and spin states of the molecule. This solution is as close as possible to the objects under study, in particular, alginate-pectin-calcium complexes. Beside this, the presented models are applicable to a larger system, taking into account random molecular structures also.

The presented models require elaboration. Semi-empirical calculation methods were used for this. It is most expedient to continue calculations by the method M062x. It is necessary that several additional principles are fulfilled:

1. The results obtained for a system consisting of a minimum molecules set at an infinite distance from each other must correspond to the sum of the results obtained for isolated molecules of this system.

2. Energy, determined by this method, is the upper limit of the electron equation exact solution. The refinements, which were carried out by semi-empirical methods, made it possible to obtain smaller values of the energy than the obtained by molecular mechanic methods models.

Geometric parameters of chelate complexes «uronate polysaccharides – Ca^{2+} » that isolated from Z-matrices for optimized molecules of CaGal_4 , CaGal_4 , $\text{CaGal}_2\text{Gal}_2$ given in Table 1. Subsequently, using the theory of the density functional in the approximation B3LYP with the following modifications: M06, M062X, peculiarities the conformational transformations of uronate polysaccharides complexes with calcium were studied.

The lengths of bonds, torsion angles and valence angles were considered as geometric parameters.

Concerning the construction of macromolecular structures, in particular uronate polysaccharides, it is

fair to say, that in Table 1 the characteristics of the complexes are visually represented: the lengths of the calcium ion with polysaccharides coordination bonds, torsion and valence angles.




Fig. 1 – Models of stable calcium-uronate systems: a – tetrahyuronate calcium (CaGul₄); b – tetragalacturonate calcium (CaGal₄); c – digalacturonotadigalacturonate calcium (CaGul₂Gal₂)

Table 1 – Geometric parameters of the system «uronate polysaccharides – Ca²⁺ chelate complexes»

		Complex													
		CaGul ₄				CaGal ₄		CaGul ₂ Gal ₂							
		n	d	n	d	n	d	n	d						
Length of bond Ca-O _n , Å		12	2.54038	53	2.54156	30	2.46918	38	2.53946						
		78	2.52733	37	2.52801	12	2.42611	8	2.49132						
		79	2.49019	38	2.49077	72	2.46897	55	2.48009						
		49	2.48383	8	2.48322	54	2.42532	75	2.43800						
		W-X-Y-Z				W-X-Y-Z		W-X-Y-Z							
Torsion angles H _w – C _x – O _y – C _z , °		φ		76-65-50-43		-61.15840		36-26-13-2		46.61303		79-69-56-45		-101.31086	
		φ		35-24-9-2		-61.15783		78-68-55-44		46.63952		35-24-9-2		-52.91515	
		ψ		52-43-50-65		22.59891		1-2-13-26		20.04796		44-45-56-69		-6.15302	
		ψ		11-2-9-24		22.59878		43-44-55-68		19.94151		11-2-9-24		15.11548	
Valence angles O _n – Ca – O _m , °		n-m		12-37		114.60009		12-30		76.79737		75-55		76.07383	
		n-m		8-38		115.46188		72-54		76.77659		38-8		106.73409	
		n-m		78-53		114.58527		-		-		-		-	
		n-m		79-49		115.44966		-		-		-		-	
		n-m		49-38		94.79095		72-12		99.95322		75-38		85.60411	
		n-m		54-37		92.60015		54-30		99.70507		55-8		99.93691	
		n-m		78-12		92.63874		-		-		-		-	
		n-m		79-8		94.79806		-		-		-		-	

Results and discussion

In the model of the complex CaGul_4 all links are equal with a small deviation within the permissible error $2,54038 \pm 0,05716 \text{ \AA}$.

Considering the model of the system CaGal_4 , the values of the calcium bonds lengths with the oxygen atoms of the nearby carboxyl and hydroxyl groups have found a similar tendency. An average value of the bond length is $2,51283 \text{ \AA}$ with permissible deviations within $\pm 0,04386 \text{ \AA}$. Comparing these indicators during the examination of the complex $\text{CaGul}_2\text{Gal}_2$, the average value of the bond length is somewhat smaller. This may indicate greater homogeneity and lower voltage of the binding atoms and more stable position. Thus, the average value of the bond length within the permissible error is $2,43800 \pm 0,04386 \text{ \AA}$.

Estimating the value of the bond length between the residues of uronic acids of polysaccharides with calcium in the complex $\text{CaGul}_2\text{Gal}_2$, it can be noticed, that these values for alginate and pectin have shifted towards the averaging. This is absolutely correct and natural as a result of the binding energies distribution in the system.

Torsion angles of the glycosidic bond were taken (as example of the system $\text{CaGul}_2\text{Gal}_2$) angle φ for atoms $\text{H}_{76}-\text{C}_{65}-\text{O}_{50}-\text{C}_{43}$ and angle ψ for atoms $\text{H}_{52}-\text{C}_{43}-\text{O}_{50}-\text{C}_{65}$ with quantitative characteristics - $101,31086$ and - $6,15302 \text{ \AA}$ respectively (Fig. 2). It is worth noting, that torsion angles for chains of different polysaccharides are very different from each other and the difference is $48,39571$ and $21,2685 \text{ \AA}$.

At the same time in the systems CaGal_4 and CaGul_4 , torsion angles φ and ψ have very similar meanings: $46,62623 \pm 0,0132 \text{ \AA}$ and $-61,158115 \pm 0,00028 \text{ \AA}$ respectively.




Fig. 2 – Fragment of the model $\text{CaGul}_2\text{Gal}_2$ with the notation of torsion angles φ and ψ ($\text{H}_w-\text{C}_x-\text{O}_y-\text{C}_z$)

Significant differences in torsion and valence angles in the system model $\text{CaGul}_2\text{Gal}_2$ connected with the geometry of uronate polysaccharides dimers. Guluronate remains have a more spatial structure, but galacturonate are more linear. In both structures ionotropic gel formation with the calcium ions participation proceeds successfully, as in the case of homogeneous uronate systems (alginate or pectinic).




Fig. 3 – Fragment of the model $\text{CaGul}_2\text{Gal}_2$ with the notation of valence angles $\text{O}_n-\text{Ca}-\text{O}_m$

The valence angle with Ca, formed in the field of one ugonate polysaccharide and various, given on Fig. 3 (as example of the angle $\text{O}_{79}-\text{Ca}-\text{O}_{49}$ and angle $\text{O}_{79}-\text{Ca}-\text{O}_{12}$).

Conclusions

It is of fundamental importance for understanding the chemistry of the ionotropic gel formation in systems of such polysaccharides, as low esterified amidated pectin and high-guluronate sodium alginate and their compositions, are the spatial arrangement of the set of atoms in these systems; the magnitude and location of bond lengths; values of torsion and valence angles. All of this in a case allows estimating the chemical activity of fragments macromolecules structures in the case of the ionotropic gel formation. This makes it possible to predict the amount of out-bound water, to calculate the optimum proportions of substances for the rational food recipes.

The fact of the ionotropic gel formation in a combined system “alginate-pectin-Ca” was established based on the obtained models and their geometric characteristics.

Chelate complex $\text{CaGul}_2\text{Gal}_2$, which formed, stable during storage, more plastic, softer as opposed to CaGul_4 and stronger than CaGal_4 .

Bibliography

1. **Кондратюк, Н. В.** Науково-практичні аспекти виробництва харчових наноплівочок на основі композицій уронатних полісахаридів / **Н. В. Кондратюк, Є. П. Пивоваров, Т. М. Степанова** // *Зб. тез доп. Міжнар. наук.-практ. конф. «Технології харчових продуктів і комбікормів»*, (Одеса, 25-30 вересня 2017 р.) / *Одеська нац. акад. харч. технологій*. – Одеса: ОНАХТ, 2017. – С.88-89 с.
2. **Brassesco, M. E.** Control of the adsorption properties of alginate - guar gum matrix functionalized with epichlorohydrin through the addition of different flexible chain polymers as toll for the chymotrypsinogen isolation / **M. E. Brassesco, N. Voitovich Valetti, G. A. Picó** // *International Journal of Biological Macromolecules*. – 2018. – V. 96. – P. 494–500. – doi:10.1016/j.ijbiomac.2018.04.087.
3. **Brassesco, M. E.** Molecular mechanism of lysozyme adsorption onto chemically modified alginate guar gum matrix / **M. E. Brassesco, N. Voitovich Valetti, G. A. Picó** // *International Journal of Biological Macromolecules*. – 2017. – V. 115. – P. 111–117. – doi:10.1016/j.ijbiomac.2016.12.029.
4. **Salama, H. E.** Novel biodegradable and antibacterial edible films based on alginate and chitosan biguanidine hydrochloride / **H. E. Salama, M. S. Abdel Aziz, M. W. Sabaa** // *International Journal of Biological Macromolecules*. – 2018. – V. 116. – P. 443–450. – doi:10.1016/j.ijbiomac.2018.04.183.
5. **Zayed, M.** Microgels of silylated HPMC as a multimodal system for drug co-encapsulation / **M. Zayed, C. Tourne-Peteilha, M. Ramondad, G. Rethorec, etc.** // *International Journal of Pharmaceutics*. – 2017. – V. 532. – 2. – P. 790–801. – doi:10.1016/j.ijpharm.2017.07.074.
6. **Dumont, M.** Processing and antibacterial properties of chitosan-coated alginate fibers / **M. Dumontac, R. Villetb, M. Guirandb, A. Montembaulta, etc.** // *Carbohydrate Polymers*. – 2018. – V. 190. – P. 31–42. – doi:10.1016/j.carbpol.2017.11.088.
7. **Оковитий, С. І.** Дослідження харчових систем на основі пектину. Квантово-хімічне моделювання димерів галактуранової кислоти / **С. І. Оковитий, Є. П. Пивоваров, Н. В. Кондратюк та ін.** // *Вісник Нац. техн. ун-ту «ХПІ» : зб. наук. пр. Темат. вип. : Нові рішення в сучасних технологіях*. – Харків : НТУ «ХПІ». – 2017. – № 7 (1229). – С. 194–198. – doi:10.20998/2413-4295.2017.07.27.
8. **Kondratjuk, N. V.** Rheological properties of food film-forming gels on the basis of uroconate polysaccharides / **N. V. Kondratjuk, Y. P. Pyvovarov, A. M. Padalka, Y. A. Polivanov** // *Bulletin of NTU "KhPI": Innovative research in students' scientific work*. – 2017. – № 41 (1263). – P. 47-51. – doi:10.5281/zenodo.1108538.
9. **Kondratjuk, N. V.** The food envelop forming coating using on the base of urinate polysaccharides in manufacture of chocolate products with protein hydrolyzate / **N. V. Kondratjuk, T. M. Stepanova, V. G. Burak** // *The development of technocal sciences: problems and solution: Conference Proceedings, April 27-28, 2018*. Brno: Baltija Publishing. – P. 53-58.
10. **Кондратюк, Н. В.** Використання гелів харчових плівкоутворюючих на основі суміші уронатних полісахаридів у виробництві оболочок для рибних закусок. / **Н. В. Кондратюк** // *Вчені записки ТНУ імені В.І. Вернадського. Серія: технічні науки*. – 2018. – Т. 29 (68). – Ч. – 3. – № 1. – С. 48-52.
11. **Nešića, A.** Design of pectin-sodium alginate based films for potential healthcare application: Study of chemico-physical interactions between the components of films and assessment of their antimicrobial activity / **A. Nešića, A. Onjiaa, S. Davidovič, etc.** // *Carbohydrate Polymers*. – 2017. – V. 157. – P. 981-990. – doi:10.1016/j.carbpol.2016.10.054.
12. **Rezvaniana, M.** Optimization, characterization, and in vitro assessment of alginate-pectin ionic cross-linked hydrogel film for wound dressing applications / **M. Rezvaniana, N. Ahmadb, etc.** // *International Journal of Biological Macromolecules*. – 2017. – V. 97. – P. 131-140. – doi:10.1016/j.ijbiomac.2016.12.079.
13. **Игнатов, С. К.** Квантово-химическое моделирование молекулярной структуры, физико-химических свойств и реакционной способности. (Часть 1. Обзор современных методов электронной структуры и теории функционала плотности). *Уч.-метод. Мат. по программе повышения квалификации «Новые материалы электроники и оптоэлектроники для информационно-телекоммуникационных систем»*. Нижний Новгород. – 2006. – С. 7 – 9.
14. **Frisch, M. J.** e. a. GAUSSIAN-09, Rev. C.01. Wallingford CT: Gaussian, Inc./ **M. J. Frisch, G. W. Trucks, H. B. Schlegel**. 2010.
15. **Андреева, Т. А.** Влияние гибридных потенциалов метода DFT на результаты исследования жидкокристаллической фазы вещества / **Т. А. Андреева, М.Е. Бедрина** // *Вестник СПбГУ. Сер. 10*. – 2015. – Вып. 1. – С. 16- 24.

Bibliography (transliterated)

1. **Kondratjuk, N. V., Pyvovarov, E. P., Stepanova, T. M.** Naukovo-praktychni aspekty vyrobnytstva kharchovykh nanoplivok na osnovi kompozytsiy uronatnykh polisakharydiv [Scientific and practical aspects of production of food nano-films on the basis of compositions of uranium polysaccharides]. *Zb. tez dop. Mizhnar. nauk.-prakt. konf. «Tekhnolohiyi kharchovykh produktiv i kombikormiv», Odesa, 25-30 veresnya 2017 r.) [Collection of those reports of the international scientific and practical conference "Technology of food and feed" Odessa, 25-30 september 2017]*. Odesa: ONAKhT, 2017, 88-89.
2. **Brassesco, M. E., Voitovich Valetti, N., Picó, G. A.** Control of the adsorption properties of alginate - guar gum matrix functionalized with epichlorohydrin through the addition of different flexible chain polymers as toll for the chymotrypsinogen isolation. *International Journal of Biological Macromolecules*, 2018, **96**, 494–500, doi:10.1016/j.ijbiomac.2018.04.087.
3. **Brassesco, M. E., Voitovich Valetti, N., Picó, G. A.** Molecular mechanism of lysozyme adsorption onto chemically modified alginate guar gum matrix. *International Journal of Biological Macromolecules*, 2017, **115**, 111–117, doi:10.1016/j.ijbiomac.2016.12.029.

4. **Salama, H. E., Aziz, M. S. A., Sabaa, M. W.** Novel biodegradable and antibacterial edible films based on alginate and chitosan biguanidine hydrochloride. *International Journal of Biological Macromolecules*, 2018, **116**, 443–450, doi:10.1016/j.ijbiomac.2018.04.183.
5. **Zayed, M., Tourne-Peteilha, C., Ramondad M., Rethorec G., etc.** Microgels of silylated HPMC as a multimodal system for drug co-encapsulation. *International Journal of Pharmaceutics*, 2017, **2**(532), 790–801, doi:10.1016/j.ijpharm.2017.07.074.
6. **Dumontac, M., Villetb, R., Guirandb M., etc.** Processing and antibacterial properties of chitosan-coated alginate fibers. *Carbohydrate Polymers*, 2018, **190**, 31–42, doi:10.1016/j.carbpol.2017.11.088.
7. **Okovytyy, S. I., Pivovarov, Y. P., Kondratjuk, N. V., Polivanov, Y. A., Bilichenko, M. O.** Research of food systems based on pectin. Quantum-chemical modeling of galacturonic acid dimers. *Bulletin of NTU "KhPI". Series: New solutions in modern technologies.* – Kharkiv: NTU "KhPI", 2017, **7** (1229), 194–198, doi:10.20998/2413-4295.2017.07.27.
8. **Kondratjuk, N. V., Pyvovarov, Y. P., Padalka, A. M., Polivanov, Y. A.,** Rheological properties of food film-forming gels on the basis of uroconate polysaccharides. *Bulletin of NTU "KhPI": Innovative research in students' scientific work*, 2017, **41**(1263), 47-51, doi:10.5281/zenodo.1108538.
9. **Kondratjuk, N. V., Stepanova, T. M., Burak, V. G.** The food envelop forming coating using on the base of urinate polysaccharides in manufacture of chocolate products with protein hydrolysate. *The development of technocal sciences: problems and solution: Conference Proceedings, April 27-28, 2018.* Brno: Baltija Publishing, 2018, 53-58.
10. **Kondratjuk, N. V.** Vykorystannya heliv kharchovykh plivkoutvoryuyuchykh na osnovi sumishi uronatykh polisakharydiv u vyrobnytstvi obolonok dlya rybnykh zakusok [Use of gel-based food-based film-forming based on a mixture of low-grade polysaccharides in the production of shells for fish snacks.]. *Vcheni zapysky TNU imeni V.I. Vernads'koho. Seriya: tekhnichni nauky [Scientific notes of TNU named after V.I. Vernadsky Series: Engineering]*, 2018, **29**(68), 3, **1**, 48-52.
11. **Nešića, A., Onjiaa, A., Davidovič, S., etc.** Design of pectin-sodium alginate based films for potential healthcare application: Study of chemico-physical interactions between the components of films and assessment of their antimicrobial activity. *Carbohydrate Polymers*, 2017, **157**, 981-990, doi:10.1016/j.carbpol.2016.10.054.
12. **Rezvaniana, M., Ahmadb, N., etc.** Optimization, characterization, and in vitro assessment of alginate-pectin ionic cross-linked hydrogel film for wound dressing applications. *International Journal of Biological Macromolecules*, 2017, **97**, 131-140, doi:10.1016/j.ijbiomac.2016.12.079.
13. **Ignatov, S. K.** Kvantovo-khimicheskoye modelirovaniye molekulyarnoy struktury, fizikokhimicheskikh svoystv i re-aktsionnoy sposobnosti Chast' 1. Obzor sovremennykh meto-dov elektronnoy struktury i teorii funktsionala plotno-sti [Quantum-chemical modeling of molecular structures, physico-chemical properties and reactivity. (Part 1. Review of modern methods of electronic structure and the theory of density functional)]. *Uch.-metod. mat. [Educational and methodological materials]*. Nizhniy Novgorod, 2006, 7-9.
14. **Frisch, M. J., Trucks, G. W., Schlegel, H. B. e. a.** GAUSSIAN-09, Rev. C.01. Wallingford CT: Gaussian, Inc., 2010.
15. **Andreyeva, T. A., Bedrina, M. E.** Vliyaniye gibridnykh potentsialov metoda DFT na rezul'taty issledovaniya zhidkokristallicheskoy fazy veshchestva [Influence of hybrid potentials of the DFT method on the results of the investigation of the liquid crystal phase of matter]. *Vestnik SPbGU [Bulletin SPbGU]. S. 10*, 2015, **1**, 16-24.

Сведения об авторах (About authors)

Кондратюк Наталія Вячеславівна – кандидат технічних наук, доцент, Дніпровський національний університет імені Олеся Гончара, доцент кафедри харчових технологій; м. Дніпро, Україна; e-mail: kondratjukn3105@gmail.com.

Natalia Kondratjuk – Associate Professor, PhD Department of Food Technology, Oles Honchar Dnipro National University, Dnipro, Ukraine; e-mail: kondratjukn3105@gmail.com.

Пивоваров Євген Павлович – доктор технічних наук, професор, Харківський державний університет харчування та торгівлі, професор кафедри технології харчування; м. Харків, Україна; e-mail: pclub@ukr.net.

Evgen Pivovarov – Doctor of Technical Sciences, Professor, Department of Technology of the food, Kharkiv State University of Food Technology and Trade, Kharkiv, Ukraine; e-mail: pclub@ukr.net.

Степанова Тетяна Михайлівна – кандидат технічних наук, доцент, Сумський національний аграрний університет, м. Суми, Україна; email: eshkina97@gmail.com.

Tatiana Stepanova – Associate Professor, Department of Food Technologies, Sumy National Agrarian University, Sumy, Ukraine; email: eshkina97@gmail.com.

Толошній Данило Вікторович – Дніпровський національний університет імені Олеся Гончара, студент 3 курсу кафедри харчових технологій; м. Дніпро, Україна.

Danylo Toloshnyi – Oles Honchar Dnipro National University, student 3th years of the Department of Food Technology, Dnipro, Ukraine.

Поливанов Єгор Андрійович – Дніпровський національний університет імені Олеся Гончара, студент 3 курсу кафедри харчових технологій; м. Дніпро, Україна.

Yehor Polyvanov – Oles Honchar Dnipro National University, student 3th years of the Department of Food Technology, Dnipro, Ukraine.

Please cite this article as:

Kondratjuk, N., Pivovarov, E., Stepanova, T., Toloshnyi, D., Polyvanov, Y. Quantum-chemical modeling of molecular complexes structure in "Uronic polyesacharides – Ca²⁺" system. *Bulletin of NTU "KhPI". Series: New solutions in modern technologies.* – Kharkiv: NTU "KhPI", 2018, **26** (1302), 2, 71–77, doi:10.20998/2413-4295.2018.26.35.

Пожалуйста, ссылайтесь на эту статью следующим образом:

Кондратюк, Н. В. Квантово-химическое моделирование структур молекулярных комплексов в системе «Уронатные полисахариды – Ca²⁺» / **Н. В. Кондратюк, Е. П. Пивоваров, Т. М. Степанова, Д. В. Толошний, Е. А. Поливанов** // *Вестник НТУ «ХПИ», Серия: Новые решения в современных технологиях.* – Харьков: НТУ «ХПИ». – 2018. – № 26 (1302). – Т. 2. – С. 71–77. – doi:10.20998/2413-4295.2018.26.35.

Будь ласка, посилайтесь на цю статтю наступним чином:

Кондратюк, Н. В. Квантово-хімічне моделювання структур молекулярних комплексів у системі «Уронатні полісахариди – Ca²⁺» / **Н. В. Кондратюк, Е. П. Пивоваров, Т. М. Степанова, Д. В. Толошний, Е. А. Поливанов** // *Вісник НТУ «ХПИ», Серія: Нові рішення в сучасних технологіях.* – Харків: НТУ «ХПИ». – 2018. – № 26 (1302). – Т. 2. – С. 71–77. – doi:10.20998/2413-4295.2018.26.35.

АНОТАЦІЯ Проведено квантово-хімічне моделювання процесу іонотропного гелеутворення в системах уронатних полісахаридів (альгіната натрія високогулуронатного і пектина низькоетерифікованого амідованого) з кальцієм. Розрахунок взаємодії активних функціональних груп уронатних полісахаридів з іоном кальцію пояснює можливість протікання даного процесу з утворенням наступних хелатних комплексів: кальцій-гулуронатного (CaGul₄), кальцій-галактуронатного (CaGal₄) та кальцій-гулуронат-галактуронатного (CaGal₂Gul₂).

У статті повідомляється про те, що процес взаємодії здійснюється за рахунок хімічного зв'язування карбоксильних та гідроксильних груп уронатних полісахаридів з іоном металу. Встановлено, що кальцій-гулуронатний комплекс має вісім точок зв'язування з іоном кальцію, а комплекси кальцій-галактуронатний та кальцій-гулуронат-галактуронатний – по чотири. Описані довжини зв'язків, величини торсійних кутів та кутів O_n-Ca-O_m в одержаних хелатних комплексах.

Ключові слова: альгінат; пектин; комплексоутворення; квантово-хімічне моделювання.

Поступила (received) 02.07.2018