

In the next stage, samples of the coal charge loaded into the hoppers of the coal-charging machine were taken from different sections and rows of the coal tower over six hours. The final stage involved analyzing the collected samples, comparing the results, and forming conclusions.

### References

1. Y. Zhao, X. Yang, Z. Luo, et al, Progress in developments of dry coal beneficiation, Int. J. Coal Sci. Technol., 1, 2014, 103–112. <https://doi.org/10.1007/s40789-014-0014-5>.
2. G. L. R. Silva, E. Destro, R. F. Bueno, J. L. de R. Oliveira, R.D. Assis, Chemical, physical and metallurgical characterization of the granulometric fractions of the coal mixture from Gerdau Açominas, Iron Ore and Raw Materials Reduction Seminar and 10th Brazilian Iron Ore Symposium, Ouro Preto: 2009, ISSN: 2594-357X. DOI 10.5151/2594-357X-15521, (in Portuguese).
3. D.V. Miroshnichenko, N.A. Desna, V.V. Koval, S.V. Fatenko, Hardgrove grindability of coal. part 1. correlations with composition, structure, and properties, Coke Chem., 62, 1, 2019, 1–4. <https://doi.org/10.3103/S1068364X19010058>.

УДК 662.92:678

## STUDY OF THE PYROLYSIS PROCESS OF HOUSEHOLD POLYMER WASTE

Vladimir Lebedev,<sup>1</sup> Serhii Kopylov,<sup>1</sup> Kateryna Rudneva,<sup>2</sup> Denis Miroshnichenko,<sup>3</sup>  
Anna Cherkashyna,<sup>1</sup> Mykhailo Miroshnychenko<sup>3</sup>

<sup>1</sup>*Department of plastics and biologically active polymers technology, National Technical University, Ukraine*

<sup>2</sup>*Sector of physical and chemical research, National Scientific Center, Hon. Prof. M. S. Bokarius Forensic Science Institute, Ukraine*

<sup>3</sup>*Department of oil, gas and solid fuel refining technologies, National Technical University, Ukraine*

*Abstract The research aims to study the functional and monomer composition of the obtained samples of pyrolysis products from the most common household polymer waste to determine the possibility of their use in industrial technologies using chromatography. The analysis of modern methods for recycling household polymer waste allows us to establish that one of the promising methods is their thermochemical decomposition (destruction) by pyrolysis. It has been shown that in the process of pyrolysis of a mixture of polymer waste, plastic waste decomposes into liquid and gaseous fractions with the release of a solid residue, the amount of which depends on the degree of contamination of the waste and the type of plastic. It has been established that the main part of plastic waste includes products of thermal destruction of polyethylene, polypropylene and polyethylene terephthalate and they are 90-95% represented by unbranched alkanes and alkenes.*

**Keywords:** *pyrolysis, household polymer waste, products, chromatography, research*

Household polymer waste (HPO) belongs to the category of municipal solid waste (MSW). There are two main methods of elimination: passive - disposal at landfills; and active - burning. The most widespread method is landfill burial (98%).<sup>1</sup> Despite the relative simplicity of this method, it has the following disadvantages: irretrievable loss of waste fractions, removal of large areas of land from circulation

for a long period, and significant costs for carrying out the necessary sanitary and epidemiological protective measures. The greatest disadvantage of solid waste disposal at landfills is associated with the existence of a real danger of contamination of drinking water aquifers. These polygons fill up quickly due to the large volume and low density of contained waste. The looseness and low compressibility of plastic waste lead to frequent landfill fires. Of the active methods of solid waste elimination, the fire (flame) combustion method is mainly used.<sup>2,3</sup> Combustion is carried out in furnaces and furnaces of various designs. In this case, a distinction is made between layered combustion of unsorted waste in the furnaces of boilers of waste incineration plants and chamber combustion of specially prepared (enriched) waste, which has a relatively stable fractional composition, in the furnaces of energy boilers or cement kilns.<sup>4,5</sup> In practice, it has been established that during flame combustion, fine dust (25-50 kg/t of waste) and gases containing carbon dioxide, nitrogen oxides, sulfur, hydrogen chloride and hydrogen fluoride, organic compounds (aldehydes and phenols), extremely toxic, are released into the atmosphere. organochlorine compounds (dioxin and furan), as well as heavy metal compounds.<sup>6,7</sup> The analysis of modern methods of recycling HPO allows us to establish that one of the promising methods is their thermochemical decomposition (destruction) by pyrolysis.<sup>8,9</sup> This method is carried out in special reactors and is more environmentally friendly and energyefficient. It is characterized by a high intensity of thermochemical transformation and an optimally structured relationship between controlled energy product flows throughout the entire technological cycle, which ensures extremely high energy efficiency values (86%).<sup>10,11</sup> The research aims to study the functional and monomer composition of the obtained samples of pyrolysis products from the most common HPOs to determine the possibility of their use in industrial technologies using chromatography. Material and methods Household polymer waste was used in the form of a mixture of waste plastic bags, polypropylene disposable tableware and polyethene terephthalate bottles in the proportion of 30:30:40% wt., respectively. The HPO pyrolysis technique included adding 100 g of BPO and placing it in a Wurtz flask, pre-weighed on a technical balance.

A water cooler and a receiver (also pre-weighed on a technical balance) are connected to the Wurtz flask. Then the BPO is heated to a temperature of at least 350 °C. Low molecular weight liquid hydrocarbon products are collected in a receiver during the process of thermal condensation in a water refrigerator. The thermal condensation temperature is controlled by a thermometer. After the appearance of the first drops of condensate, reduce the heating speed. The heating of the flask is adjusted so that the pyrolysis rate does not exceed 1 drop per second. The experiment was continued at a temperature in the heating mantle not higher than 350 °C until the end of the process of separation of low molecular weight liquid hydrocarbon products, which can be judged by the cessation of condensate formation. The liquid products of HPO pyrolysis composition were determined by the standard gas-liquid chromatography method on a Shimadzu chromatograph (Japan). Evaporator temperature – 240 °C; detector temperature – 250 °C; speed of carrier gas (hydrogen) – 1.0 ml/min., flow division – 1:60. Fatty acids were identified by comparing their retention times with the retention times of reference samples.

Thus, in the process of pyrolysis of a mixture of polymer waste, plastic waste decomposes into liquid and gaseous fractions with the release of a solid residue, the amount of which depends on the degree of contamination of the waste and the type of plastic. It has been established that the main part of plastic waste includes products of thermal destruction of polyethylene, polypropylene and polyethylene terephthalate and they are 90-95% represented by unbranched alkanes and alkenes. In general, the liquid fraction containing light and heavy hydrocarbons can be used to produce liquid fuels and wax, the latter being used, for example, in the manufacture of cables and capacitors. The solid residue can be used in construction as a good waterproofing agent; after mixing it with sand and crushed stone, obtaining a highstrength paving slab coating is possible. One of the important areas of application of semi-liquid products of pyrolysis of plastic waste may be their use as raw materials followed by hydrodealkylation to obtain diesel fuel components with high cetane numbers and ultra-low sulfur and aromatic hydrocarbons content.

### References

1. Damayanti D, Saputri D, Marpaung D, et al. Current prospects for plastic waste treatment. *Polymers*. - 2022;-14(15):3133.
2. Prajapati R, Kohli K, Maity S, et al. Recovery and recycling of polymeric and plastic materials. In recent developments in plastic recycling. Springer. Singapore; 2021:15–41.
3. Epure E, Cojocaru F, Aradoaei M, et al. Exploring the surface potential of recycled polyethylene terephthalate composite supports on the collagen contamination level. *Polymers*. - 2023; - 15(3):776.
4. Gaidhani A, Mahanwar P. Conversion of waste polyolefins to polyethylene wax via pyrolysis. *Energy Sources, Part A: Recovery, Utilization, and Environmental Effects*. - 2023;45(1):2112–2121.
5. Pan D, Su F, Liu H, et al. Research progress on catalytic pyrolysis and reuse of waste plastics and petroleum sludge. *ES Mater & Manuf*. - 2021;(11):3–15.
6. Fulgencio Medrano L, Garcia Fernandez S, Asueta A, et al. Oil production by pyrolysis of real plastic waste. *Polymers*. - 2022;(14): 553.
7. Ahmad I, Khan M, Khan H et al. Pyrolysis study of polypropylene and polyethylene into premium oil products. *Int J Green Energy*. - 2015;12(7):663–671.
8. Harussani M, Sapuan S, Rashid U, et al. Pyrolysis of polypropylene plastic waste into carbonaceous char: Priority of plastic waste management amidst COVID-19 pandemic. *Sci Total Environ*. - 2022; - (803):149911.
9. Miandad R, Rehan M, Barakat M, et al. Catalytic pyrolysis of plastic waste, moving toward pyrolysis based biorefineries. *Front Energy Res*. - 2019;- 7(7):27.
10. Grigorov A. The prospects of obtaining plastic greases from secondary hydrocarbon raw material. *Pet Coal*. - 2018;- 60(5):879–883.
11. Grigorov A, Sinkevich I, Ponomarenko N, et al. Recycling of polymer waste into plastic lubricants. *Pet Coal*. - 2022;64(3):709–713.